



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Shield Arctic Pre Stretch Technical Data Sheet

- Excellent Cling at low temperatures
- Lightweight & Ergonomic
- Reinforced edges make it nick proof
- Product Categories – SAPHF

Thickness	ASTM D-4649	Gauge	33
Tensile Ultimate MD	ASTM D-882	PSI	16000
Tensile Ultimate TD	ASTM D-882	PSI	4200
Tensile Yield MD	ASTM D-882	PSI	7450
Tensile Yield TD	ASTM D-882	PSI	1500
Elongation MD	ASTM D-882	%	200
Elongation TD	ASTM D-882	%	710
Elmendorf Tear MD	ASTM D-1922	g/mil	180
Elmendorf Tear TD	ASTM D-1922	g/mil	680
Puncture Force	WRAP-TITE	LBS	-
Cling@200%	ASTM D-5458	g/in	185



- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, **B2B:** www.wraptite.com
Head Quarters: 6200 Cochran Road, Solon, Ohio 44139
Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/
Manufacturing: 6075 Cochran Road, Solon, Ohio 44139
Fax: 440-349-5432