



Your Source for Industrial Packaging, Jan/San and Safety Supplies



Ultra-High Performance Machine Film Technical Data Sheet

- High level puncture resistance
- Unparalleled load retention in thin-gauge materials
- Strong, high-performance film with a wide range of applications

	WT Item ID		UHPMF2065AM	UHPMF2070AM	UHPMF2080AM	UHPMF2090AM
Thickness	ASTM D-4649	Gauge (Mic)	10	11	12	13
Tensile Ultimate MD	ASTM D-882	PSI	4351	4496	4641	4931
Tensile Ultimate TD	ASTM D-882	PSI	2610	4351	4351	4351
Tensile Yield MD	ASTM D-882	PSI	1305	1305	1305	1305
Tensile Yield TD	ASTM D-882	PSI	1015	1189	1189	1189
Elongation MD	ASTM D-882	%	448	500	521	550
Elongation TD	ASTM D-882	%	607	660	699	715
Puncture Force	WRAP TITE	LBS	4.95	4.95	4.95	4.95
Cling@200%	WRAP TITE	Grams	13.85	13.85	13.85	13.85

All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.

Email: info@wraptite.com / **B2B:** www.wraptite.com

Corporate HQ: 6200 Cochran Rd., Solon, OH 44139

Phone: (888) 972-7848 / (440) 349-5400

Manufacturing Website: www.wraptite.com/manufacturing

Mfg. Plant: 6250 Camp Industrial Rd., Solon, OH 44139

Fax: (440) 349-5432