



3" Cast Extended Core Stretch Film



Product Data Sheet

Effective 01/2017

Item ID Numbers:

CEX380A, CEX380F1, CEX380F, CEX380E1, CEX380E, CEX380G1, CEX380G, CEX390A, CEX390G1, CEX390G, CEX310A, CEX312A, CEX312G1, CEX312G, CEX315A

Nominal Values:

Film Properties	ASTM Test Method	80 Gauge	90 Gauge	100 Gauge	120 Gauge	150 Gauge
Tensile @ Break MD (psi)	D-882	6,300	6,300	6,300	6,300	6,350
Tensile @ Break TD (psi)	D-882	4,100	4,200	4,100	4,100	4,100
Tensile @ Yield MD (psi)	D-882	1,350	1,350	1,350	1,350	1,330
Tensile @ Yield TD (psi)	D-882	1,200	1,200	1,200	1,200	1,200
Elongation MD (%)	D-882	560	500	510	540	540
Elongation TD (%)	D-882	620	600	590	650	650
Elmendorf Tear MD (g/mil)	D-1922	330	330	330	330	330
Elmendorf Tear TD (g/mil)	D-1922	550	570	540	550	540
Core Properties						
Length		8"	8"	8"	8"	8"
Diameter		1.3"	1.3"	1.3"	1.3"	1.3"
Wall Thickness		125 MIL	125 MIL	125 MIL	125 MIL	125 MIL
Remark:	For G, G1 Core dia. 1.78", length 3", Wall Thickness 170 mil					

Wrap Tite, Inc.
6200 Cochran Rd.
Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction