



4" Cast Extended Core Stretch Film



Product Data Sheet

Effective 01/2017

Item ID Numbers:

CEX480A, CEX415A

Nominal Values:

Film Properties	ASTM Test Method	80 Gauge	150 Gauge
Tensile @ Break MD (psi)	D-882	6,125	6,300
Tensile @ Break TD (psi)	D-882	4,175	4,350
Tensile @ Yield MD (psi)	D-882	1,350	1,370
Tensile @ Yield TD (psi)	D-882	1,200	1,250
Elongation MD (%)	D-882	540	565
Elongation TD (%)	D-882	640	670
Elmendorf Tear MD (g/mil)	D-1922	310	325
Elmendorf Tear TD (g/mil)	D-1922	590	615

Core Properties

Length	8"	8"
Diameter	1.3"	1.3"
Wall Thickness	125 mil	

Wrap Tite, Inc.
6200 Cochran Rd.
Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction