



Product Data Sheet

Down Gauge Pipe Stretch Film



Effective 01/2017

Item ID Numbers:

SPW2045A, SPW2050A, SPW2055A, SPW2063A



Nominal Values: (Tol.:- +/-15%)

Properties	ASTM Test Method	45 Gauge	50 Gauge	55 Gauge	63 Gauge
Tensile @ Break MD (psi)	D-882	5,915	6,000	6,150	6,225
Tensile @ Break TD (psi)	D-882	4,100	4,135	4,215	4,300
Tensile @ Yield MD (psi)	D-882	1,285	1,325	1,350	1,370
Tensile @ Yield TD (psi)	D-882	1,180	1,200	1,200	1,220
Elongation MD (%)	D-882	512	520	525	540
Elongation TD (%)	D-882	655	670	670	690
Elmendorf Tear MD (g/mil)	D-1922	315	322	325	330
Elmendorf Tear TD (g/mil)	D-1922	615	620	620	630

Wrap Tite, Inc.
 6200 Cochran Rd.
 Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction