



### 3" Down Gauge Narrow Width Stretch Film



## Product Data Sheet

Effective 01/2017

#### Item ID Numbers:

SNW345A, SNW347A, SNW350A, SNW355A, SNW363A

#### Nominal Values:

Film Properties	ASTM Test Method	45 Gauge	47 Gauge	50 Gauge	55 Gauge	63 Gauge
Tensile @ Break MD (psi)	D-882	6,400	6,400	6,300	6,300	6,300
Tensile @ Break TD (psi)	D-882	4,200	4,200	4,200	4,100	4,100
Tensile @ Yield MD (psi)	D-882	1,350	1,350	1,350	1,350	1,420
Tensile @ Yield TD (psi)	D-882	1,230	1,230	1,200	1,200	1,250
Elongation MD (%)	D-882	610	610	550	560	540
Elongation TD (%)	D-882	780	780	600	590	650
Elmendorf Tear MD (g/mil)	D-1922	300	300	310	310	320
Elmendorf Tear TD (g/mil)	D-1922	650	650	670	670	650

**Wrap Tite, Inc.**  
6200 Cochran Rd.  
Solon, Ohio 44139  
**Toll Free:** 888-WRAP TITE (972-7848)  
**Fax:** 440-349-5432  
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction