



5" Down Gauge Narrow Width Stretch Film



Product Data Sheet

Effective 01/2017

Item ID Numbers:

SNW545A , SNW545B , SNW550A , SNW563A

Nominal Values:

Film Properties	ASTM Test Method	45 Gauge	50 Gauge	63 Gauge
Tensile @ Break MD (psi)	D-882	6,400	6,300	6,300
Tensile @ Break TD (psi)	D-882	4,200	4,200	4,100
Tensile @ Yield MD (psi)	D-882	1,350	1,350	1,420
Tensile @ Yield TD (psi)	D-882	1,230	1,200	1,250
Elongation MD (%)	D-882	610	550	540
Elongation TD (%)	D-882	780	600	650
Elmendorf Tear MD (g/mil)	D-1922	300	310	320
Elmendorf Tear TD (g/mil)	D-1922	650	670	650

Wrap Tite, Inc.
6200 Cochran Rd.
Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction