



Product Data Sheet

5" Down Gauge Cast Extended Core Stretch Film



Effective 01/2017

Item ID Numbers:

SEX545A , SEX547A , SEX550A

Nominal Values: (Tol. +/- 15%)

Film Properties	ASTM Test Method	45 Gauge	47 Gauge	50 Gauge
Tensile @ Break MD (psi)	D-882	6,400	6,400	6,300
Tensile @ Break TD (psi)	D-882	4,200	4,200	4,200
Tensile @ Yield MD (psi)	D-882	1,350	1,350	1,350
Tensile @ Yield TD (psi)	D-882	1,230	1,230	1,200
Elongation MD (%)	D-882	610	610	550
Elongation TD (%)	D-882	780	780	600
Elmendorf Tear MD (g/mil)	D-1922	300	300	310
Elmendorf Tear TD (g/mil)	D-1922	650	650	670
Core Properties				
Length		10"	10"	10"
Diameter		1.3"	1.3"	1.3"
Wall Thickness		125 MIL	125 MIL	125 MIL

Wrap Tite, Inc.

6200 Cochran Rd.
Solon, Ohio 44139

Toll Free: 888-WRAP TITE (972-7848)

Fax: 440-349-5432

www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction