



# 5" Cast Extended Core Stretch Film



Effective 01/2017

## Product Data Sheet

### Item ID Numbers:

CEX560A, CEX570A, CEX580A, CEX580C, CEX580F1, CEX580F, CEX580E1, CEX580E, CEX580G1, CEX580G, CEX590A, CEX590G1, CEX590G, CEX510A, CEX512A, CEX512G1, CEX512G

### Nominal Values:

Film Properties	ASTM Test Method	60 Gauge	70 Gauge	80 Gauge	90 Gauge	100 Gauge	120 Gauge
Tensile @ Break MD (psi)	D-882	6,500	6,500	6,300	6,300	6,300	6,300
Tensile @ Break TD (psi)	D-882	4,100	4,000	4,100	4,200	4,100	4,100
Tensile @ Yield MD (psi)	D-882	1,300	1,350	1,350	1,350	1,350	1,350
Tensile @ Yield TD (psi)	D-882	1,200	1,200	1,200	1,200	1,200	1,200
Elongation MD (%)	D-882	390	420	560	500	510	540
Elongation TD (%)	D-882	610	620	620	600	590	650
Elmendorf Tear MD (g/mil)	D-1922	350	340	330	330	330	330
Elmendorf Tear TD (g/mil)	D-1922	600	550	550	570	540	550
<b>Core Properties</b>							
Length		10"	10"	10"	10"	10"	10"
Diameter		1.3"	1.3"	1.3"	1.3"	1.3"	1.3"
Wall Thickness		125 MIL	125 MIL	125 MIL	125 MIL	125 MIL	125 MIL
Remark:		For G, G1 Core dia. 1.78", length 3", Wall Thickness 170 mil					

### Wrap Tite, Inc.

6200 Cochran Rd.

Solon, Ohio 44139

**Toll Free: 888-WRAP TITE (972-7848)**

**Fax: 440-349-5432**

[www.wraptite.com](http://www.wraptite.com) – [info@wraptite.com](mailto:info@wraptite.com)



NOTE: MD = Machine Direction

TD = Transverse Direction