



# Product Data Sheet

## Blown Hand Film



Effective 01/2017

### Item ID Numbers:

BHF1280A, BHF1580A, BHF1880A

### Nominal Values:

Properties	ASTM Test Method	80 Gauge
Tensile @ Break MD (psi)	D-882	6,800
Tensile @ Break TD (psi)	D-882	4,600
Tensile @ Yield MD (psi)	D-882	1,600
Tensile @ Yield TD (psi)	D-882	1,700
Elongation MD (%)	D-882	470
Elongation TD (%)	D-882	720
Protrusion Puncture ( lbs )	D-5748	8.8
Protrusion Puncture Energy (in-lbs)	D-5748	15.0
Elmendorf Tear MD (g/mil)	D-1922	150
Elmendorf Tear TD (g/mil)	D-1922	500
Cling – Outside to Inside @225%	D-5458	Min 150g/mil

### Wrap Tite, Inc.

6200 Cochran Rd.  
Solon, Ohio 44139

**Toll Free:** 888-WRAP TITE (972-7848)

**Fax:** 440-349-5432

[www.wraptite.com](http://www.wraptite.com) – [info@wraptite.com](mailto:info@wraptite.com)



NOTE: MD = Machine Direction

TD = Transverse Direction