



Product Data Sheet

Blown Hand Film



Effective 01/2017

Item ID Numbers:

BHF1290A, BHF1590A, BHF1890A

Nominal Values: (Tol. +/- 15%)

Properties	ASTM Test Method	90 Gauge
Tensile @ Break MD (psi)	D-882	6,700
Tensile @ Break TD (psi)	D-882	4,500
Tensile @ Yield MD (psi)	D-882	1,600
Tensile @ Yield TD (psi)	D-882	1,700
Elongation MD (%)	D-882	465
Elongation TD (%)	D-882	750
Protrusion Puncture (lbs)	D-5748	9.2
Protrusion Puncture Energy (in-lbs)	D-5748	17.0
Elmendorf Tear MD (g/mil)	D-1922	150
Elmendorf Tear TD (g/mil)	D-1922	500
Cling-Outside to Inside@225%	D- 5458	Min 150g/mil

Wrap Tite, Inc.
 6200 Cochran Rd.
 Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction