



Product Data Sheet

Blown Hand Film



Effective 01/2017

Item ID Numbers:

BHF15100A, BHF18100A

Nominal Values: (Tol. +/- 15%)

Properties	ASTM Test Method	100 Gauge
Tensile @ Break MD (psi)	D-882	6,600
Tensile @ Break TD (psi)	D-882	4,300
Tensile @ Yield MD (psi)	D-882	1,600
Tensile @ Yield TD (psi)	D-882	1,700
Elongation MD (%)	D-882	530
Elongation TD (%)	D-882	720
Protrusion Puncture (lbs)	D-5748	9.3
Protrusion Puncture Energy (in-lbs)	D-5748	22.0
Elmendorf Tear MD (g/mil)	D-1922	120
Elmendorf Tear TD (g/mil)	D-1922	750
Cling-Outside to Inside@225%	D-5458	Min.150g/mil

Wrap Tite, Inc.
 6200 Cochran Rd.
 Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction