



# High Performance Cast Machine Stretch Film



## Product Data Sheet

Effective 01/2017

### Item ID Numbers:

PMF2047A-WT, PMF2051A-WT, PMF2055A-WT, PMF2063A-WT, PMF2063B-WT ,  
PMF2063C-WT, PMF2063D-WT

### Nominal Values: (+/-15%)

| Film Properties           | ASTM Test Method | 47 Gauge | 51 Gauge | 55 Gauge | 63 Gauge |
|---------------------------|------------------|----------|----------|----------|----------|
| Tensile @ Break MD (psi)  | D-882            | 6600     | 6400     | 6500     | 6600     |
| Tensile @ Break TD (psi)  | D-882            | 4600     | 4800     | 4800     | 5200     |
| Tensile @ Yield MD (psi)  | D-882            | 1270     | 1560     | 1450     | 1420     |
| Tensile @ Yield TD (psi)  | D-882            | 1125     | 1250     | 1270     | 1250     |
| Elongation MD (%)         | D-882            | 670      | 660      | 640      | 620      |
| Elongation TD (%)         | D-882            | 710      | 650      | 630      | 780      |
| Elmendorf Tear MD (g/mil) | D-1922           | 317      | 327      | 350      | 360      |
| Elmendorf Tear TD (g/mil) | D-1922           | 615      | 620      | 620      | 635      |

**Wrap Tite, Inc.**  
6200 Cochran Rd.  
Solon, Ohio 44139  
**Toll Free: 888-WRAP TITE (972-7848)**  
**Fax: 440-349-5432**  
www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction