



# Product Data Sheet

## 8.5 Micron Pre-Stretch Film



Effective 06/2017

### Product Description:

- Engineered Cast film
- Greater than 20% savings
- Excellent cling
- Ergonomic
- Superior strength
- Nick proof edges
- Light weight
- Easy to use

### Specifications:

Item ID	Film	Length	Core	Packaging	Count per Pallet
EWNW3A	Cast	1000'	3" ID	Case	72 cases
EWNW5A	Cast	1000'	3" ID	Case	72 cases
EWHF1415A-MAX80	Cast	1476'	3" ID	Case	80 cases
EWHF1615A-MAX80	Cast	1476'	3" ID	Case	64 cases
EWHF1815A-MAX80	Cast	1476'	3" ID	Case	64 cases
EW1420A-MAX80	Cast	1968'	3" ID	Bulk	280 rolls
EW1615A-MAX80	Cast	1968'	3" ID	Bulk	240 rolls
EW1620A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW1820A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW1850A-MAX80	Cast	5000'	3" ID	Bulk	100 rolls
GW1820A	Cast	2000'	NO CORE	Bulk	168 rolls
GWNW320A	Cast	2000'	NO CORE	Case	72 cases
GWNW520A	Cast	2000'	NO CORE	Case	72 cases

Film Properties	Typical Value	Tolerance	Test Method
Tensile Strength at yield MD	No yield	+/- 15%	ASTM D882
Tensile Strength at yield TD	1100 psi	+/- 15%	ASTM D882
Tensile Strength at Break MD	16000 psi	+/- 15%	ASTM D882
Tensile Strength at Break TD	4000 psi	+/- 15%	ASTM D882
Elongation at Break MD	200%	+/- 15%	ASTM D882
Elongation at Break TD	850%	+/- 15%	ASTM D882
Elmendorf Tear Strength MD	150%	+/- 15%	ASTM D1922
Elmendorf Tear Strength TD	960%	+/- 15%	ASTM D1922

**Wrap Tite, Inc.**  
 6200 Cochran Rd.  
 Solon, Ohio 44139  
**Toll Free:** 888-WRAP TITE (972-7848)  
**Fax:** 440-349-5432  
[www.wraptite.com](http://www.wraptite.com) – [info@wraptite.com](mailto:info@wraptite.com)

