



Product Data Sheet

6.4 Micron Pre-Stretch Film



Effective 01/2017

Product Description:

- Engineered Cast film
- Greater than 20% savings
- Excellent cling
- Ergonomic
- Superior strength
- Nick proof edges
- Light weight
- Easy to use



Specifications:

Item ID	Film	Length	Core	Packaging	Count per Pallet
EWHF141506A-MAX80	Cast	1476'	3" ID	Case	80 cases
EWHF161506A-MAX80	Cast	1476'	3" ID	Case	64 cases
EWHF181506A-MAX80	Cast	1476'	3"ID	Case	64 cases
EW142006A-MAX80	Cast	1968'	3" ID	Bulk	280 rolls
EW162006A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW182006A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
Film Properties		Typical Value		Tolerance	Test Method
Tensile Strength at yield MD		No yield		+/- 15%	ASTM D882
Tensile Strength at yield TD		1100 psi		+/- 15%	ASTM D882
Tensile Strength at Break MD		16500 psi		+/- 15%	ASTM D882
Tensile Strength at Break TD		4000 psi		+/- 15%	ASTM D882
Elongation at Break MD		200%		+/- 15%	ASTM D882
Elongation at Break TD		970%		+/- 15%	ASTM D882
Elmendorf Tear Strength MD		150g/mil		+/- 15%	ASTM D1922
Elmendorf Tear Strength TD		965g/mil		+/- 15%	ASTM D1922

Wrap Tite, Inc.

6200 Cochran Rd.
Solon, Ohio 44139

Toll Free: 888-WRAP TITE (972-7848)

Fax: 440-349-5432

www.wraptite.com – info@wraptite.com

