

WRAP TITE

Product Data Sheet

8.5 Mic Color Pre-Stretch Film



Effective 01/2017

Product Description:

- Engineered Cast film
- Greater than 20% savings
- Excellent cling
- Ergonomic
- Superior strength
- Nick proof edges
- Light weight
- Easy to use

Specifications:

Item ID	Film	Length	Core	Packaging	Count per Pallet
EWHF17AB	Cast	1500'	3" ID	Case	64 cases
EWHF17AL	Cast	1500'	3" ID	Case	64 cases
EWHF17AO	Cast	1500'	3" ID	Case	64 cases
EWHF17AR	Cast	1500'	3" ID	Case	64 cases
EWHF17AG	Cast	1500'	3" ID	Case	64 cases
EWHF17AY	Cast	1500'	3" ID	Case	64 cases
EWHF17AW	Cast	1500'	3" ID	Case	64 cases

Film Properties	Typical Value	Tolerance	Test Method
Tensile Strength at yield MD	No yield	+/- 15%	ASTM D882
Tensile Strength at yield TD	1100 psi	+/- 15%	ASTM D882
Tensile Strength at Break MD	16000 psi	+/- 15%	ASTM D882
Tensile Strength at Break TD	4200 psi	+/- 15%	ASTM D882
Elongation at Break MD	200%	+/- 15%	ASTM D882
Elongation at Break TD	820%	+/- 15%	ASTM D882
Elmendorf Tear Strength MD	150 g/mil	+/- 15%	ASTM D1922
Elmendorf Tear Strength TD	960 g/mil	+/- 15%	ASTM D1922

Wrap Tite, Inc.
 6200 Cochran Rd.
 Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com

