



Product Data Sheet

7.4 Micron Pre-Stretch Film



Effective 01/2017

Product Description:

- Engineered Cast film
- Greater than 20% savings
- Excellent cling
- Ergonomic
- Superior strength
- Nick proof edges
- Light weight
- Easy to use



Specifications:

Item ID	Film	Length	Core	Packaging	Count per Pallet
EWHF141507A-MAX80	Cast	1476'	3" ID	Case	80 cases
EWHF161507A-MAX80	Cast	1476'	3" ID	Case	64 cases
EWHF181507A-MAX80	Cast	1476'	3" ID	Case	64 cases
EW142007A-MAX80	Cast	1968'	3" ID	Bulk	280 rolls
EW161507A-MAX80	Cast	1968'	3" ID	Bulk	240 rolls
EW162007A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW182007A-MAX80	Cast	1968'	3" ID	Bulk	224rolls

Film Properties	Typical Value	Tolerance	Test Method
Tensile Strength at yield MD	No yield	+/- 15%	ASTM D882
Tensile Strength at yield TD	1150 psi	+/- 15%	ASTM D882
Tensile Strength at Break MD	16500 psi	+/- 15%	ASTM D882
Tensile Strength at Break TD	4000 psi	+/- 15%	ASTM D882
Elongation at Break MD	200%	+/- 15%	ASTM D882
Elongation at Break TD	980%	+/- 15%	ASTM D882
Elmendorf Tear Strength MD	150g/mil	+/- 15%	ASTM D1922
Elmendorf Tear Strength TD	970g/mil	+/- 15%	ASTM D1922

Wrap Tite, Inc.

6200 Cochran Rd.
Solon, Ohio 44139

Toll Free: 888-WRAP TITE (972-7848)

Fax: 440-349-5432

www.wraptite.com – info@wraptite.com

