



Product Data Sheet

8.5 Micron Pre-Stretch Film



Effective 01/2017

Product Description:

- Engineered Cast film
- Greater than 20% savings
- Excellent cling
- Ergonomic
- Superior strength
- Nick proof edges
- Light weight
- Easy to use



Specifications:

Item ID	Film	Length	Core	Packaging	Count per Pallet
EWNW3A	Cast	1000'	3" ID	Case	72 cases
EWNW5A	Cast	1000'	3" ID	Case	72 cases
EWHF1415A-MAX80	Cast	1476'	3" ID	Case	80 cases
EWHF1615A-MAX80	Cast	1476'	3" ID	Case	64 cases
EWHF1815A-MAX80	Cast	1476'	3" ID	Case	64 cases
EW1420A-MAX80	Cast	1968'	3" ID	Bulk	280 rolls
EW1615A-MAX80	Cast	1968'	3" ID	Bulk	240 rolls
EW1620A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW1820A-MAX80	Cast	1968'	3" ID	Bulk	224 rolls
EW1850A-MAX80	Cast	5000'	3" ID	Bulk	100 rolls

Film Properties	Typical Value	Tolerance	Test Method
Tensile Strength at yield MD	No yield	+/- 15%	ASTM D882
Tensile Strength at yield TD	1100 psi	+/- 15%	ASTM D882
Tensile Strength at Break MD	16000 psi	+/- 15%	ASTM D882
Tensile Strength at Break TD	4000 psi	+/- 15%	ASTM D882
Elongation at Break MD	200%	+/- 15%	ASTM D882
Elongation at Break TD	850%	+/- 15%	ASTM D882
Elmendorf Tear Strength MD	150%	+/- 15%	ASTM D1922
Elmendorf Tear Strength TD	960%	+/- 15%	ASTM D1922

Wrap Tite, Inc.
 6200 Cochran Rd.
 Solon, Ohio 44139
Toll Free: 888-WRAP TITE (972-7848)
Fax: 440-349-5432
www.wraptite.com – info@wraptite.com

