



Product Data Sheet

Select Cast Machine Stretch Film



Effective 01/2017

Item ID Numbers:

CMF1060B, CMF1080B, CMF1080A, CMF2060A, CMF2070A, CMF2070B,
CMF2080A, CMF2080B, CMF3070A, CMF3070B, CMF3080A, CMF3080B, CMF30100A,
CMF30100B, CMF30110B, CMF4080A, CMF5080A, CMF5080B,
CMF6080A, CMF7080A, CMF1280A, CMF13100A, CMF1580A, CMF1580B

Nominal Values:

Film Properties	ASTM Test Method	60 Gauge	70 Gauge	80 Gauge	100 Gauge	110 Gauge
Tensile @ Break MD (psi)	D-882	6,000	6,400	6,200	6,800	6,700
Tensile @ Break TD (psi)	D-882	4,100	4,000	4,300	4,600	4,500
Tensile @ Yield MD (psi)	D-882	1,250	1,250	1,250	1,300	1,350
Tensile @ Yield TD (psi)	D-882	1,050	1,100	1,150	1,200	1,250
Elongation MD (%)	D-882	580	650	680	750	650
Elongation TD (%)	D-882	820	780	820	850	775
Elmendorf Tear MD (g/mil)	D-1922	330	325	500	300	300
Elmendorf Tear TD (g/mil)	D-1922	650	640	900	610	620

Wrap Tite, Inc.

6200 Cochran Rd.
Solon, Ohio 44139

Toll Free: 888-WRAP TITE (972-7848)

Fax: 440-349-5432

www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction